

Technical Data Sheet

Type: PE-LD (low density polyethylene) regranulate for foil extrusion

Form: Pellets

Material specifications	Standard	Unit	Value
MFR	DIN EN ISO 1133	190°C /2.16kg	0.75 – 1 (g/10min)
density	DIN EN ISO 1183	g/cm ³	0,85 - 0,90
moisture	IR- Drying scale	%	< 2
ash content	DIN EN ISO 1172	%	appx. 0,8
color	<i>colored</i>		
origin	polyethylene post-consumer/post-industrial waste packages		

Date: 13.03.2018

