

Technical Data Sheet

Type: PE-LD (low density polyethylene) regranulate for foil extrusion

Form: Pellets

| Material specifications | Standard | Unit | Value |
|--------------------------------|---|-------------------|-----------------------|
| MFR | DIN EN ISO 1133 | 190°C /2.16kg | 0.75 – 1 (g/10min) |
| density | DIN EN ISO 1183 | g/cm ³ | 0,85 - 0,90 |
| moisture | IR- Drying scale | % | < 2 |
| ash content | DIN EN ISO 1172 | % | appx. 0,8 |
| color | <i>natural</i> | | |
| origin | polyethylene post-consumer/post-industrial waste packages | | |

Date: 13.03.2018

